



Building with conscience.

StoSignature™ Color Effect: Color Partial

Application Guide

Facades



StoSignature™ Color Effect Color Partial is a technique that colors the raised areas of the texture providing a color accent that highlights the unique surface structure. StoSignature makes it easy to create your own custom surface aesthetic.



Color Effect: Color Partial

Partially colored raised textures.



Skill Level 2



Surface Description

Description	<ul style="list-style-type: none">• This is a technique for an existing texture, which coats the raised parts of that texture.
Product	<ul style="list-style-type: none">• StoColor® Acryl• StoColor® Acryl Plus
Possible Color Shades	<ul style="list-style-type: none">• StoColor® System; LRV \geq 20 for StoTherm® ci systems with EPS or XPS insulation <p>The minimum permissible light reflectance value depends on the substrate, the system, and the product.</p>



Foam Roller

Please note that the details, illustrations, general technical information, and drawings contained in this brochure are only general proposals and details which merely describe the basic functions schematically. They are not dimensionally accurate. Applicator/customer is independently responsible for determining the suitability and completeness for the product in question. Adjacent works are described only schematically. All specifications and information must be adjusted or agreed in the light of local conditions and do not constitute work, detail or installation plans. The technical specifications and product information in the Technical Data Sheets and in system descriptions/approvals must be observed.



Application Steps

Color Partial

Surfaces with partially coated raised textures.



Coat the foam roller with the desired colored coating. Then roll across a flat surface until the roller only contains a small amount of paint. The foam structure should be visible.



Carefully place the foam roller onto the surface and guide it across the raised textures using light pressure.

Notes

For a uniform effect on the facade, ensure the partially coated surfaces are irregularly offset, particularly at the transitions from scaffolding levels.

To successfully implement the Color Partial technique, it is particularly important to use a foam roller that is not completely filled when rolling over the raised texture. It is ideal if the foam texture is still easily visible.

For linear textures, only roll in the direction of the texture.

For nondirectional textures, guide the lightly filled foam roller across the area in short strokes, in a crisscross pattern.

When changing directions, lift roller off the surface.

Notes and Tips

Basic Information:

Achieving good results requires a certain degree of skill and knowledge of the trade, plus preliminary training in the relevant techniques.

Hand-held samples and sample surface areas:

Smaller samples are not always suitable for providing an overall impression of an application technique on larger facade surfaces. For this reason, we highly recommend having the contractor prepare a mock up sample. If this work requires scaffolding, this should be taken into account when creating the sample. The finished sample area should be inspected and accepted by the site manager/building owner. The area provides a reference surface for the contracted service.

Planning the work procedure and how the work is divided up:

Before starting the work, determine who will carry out which tasks such as applying, smoothing or texturing. Carefully plan each coating process, taking into account the weather conditions, and prepare the relevant material.

Uniform Application:

When tradesmen create facade textures or structures, it is important to remember that each tradesman has his or her own signature style. For smaller facade surfaces, if possible same person should create the structure or texture, in order to prevent discrepancies. On large facade surfaces, an experienced team may combine individual application techniques to produce an end result that has a harmonious appearance.

Size of the area:

For large facades, we recommend dividing the surface to be created into smaller partial areas. This ensures that calculations and execution are reliable, and that good application results will be achieved.

Scaffolding:

The scaffolding must be appropriate for the trade processes being carried out and the techniques and tools used: take into account the spacing, the brackets, the projections, and the positioning and height of the scaffolding.

Weather protection:

If the weather is unfavorable during the application and drying processes, it is necessary to put in place appropriate protective measures (rain/solar protection, etc.).

Corner areas/connections:

Carefully plan connections and corner areas. It may be necessary to use a different application technique in these areas. Not every technique is suitable for use up into internal corners, for example.

Areas with fine textured finish:

Float-finishing, smoothing, or sanding smoothed textures requires more extensive substrate preparation than in the case of rough textures. Additional measures for levelling out the substrate may be required depending on its nature.

Color schemes:

Intense or dark colors will emphasize uneven areas of the substrate, textural differences in the finish, and any other effects caused during application. For this reason, a coarser finish texture (aggregate size >2.0) is recommended for facades with intense colors or dark tints. It is important to observe project-related aspects from a technical perspective such as substrate warming and system compatibility. The color shade must be balanced to suit the substrate, system and type of use.

Sto Americas

Sto Corp.

3800 Camp Creek Pkwy
Building 1400, Suite 120
Atlanta, GA 30331
USA

Phone 1-800-221-2397
www.stocorp.com

ATTENTION

Sto products are intended for use by qualified professional contractors, not consumers, as a component of a larger construction assembly as specified by a qualified design professional, general contractor or builder. They should be installed in accordance with those specifications and Sto's instructions. Sto Corp. disclaims all, and assumes no, liability for on-site inspections, for its products applied improperly, or by unqualified persons or entities, or as part of an improperly designed or constructed building, for the nonperformance of adjacent building components or assemblies, or for other construction activities beyond Sto's control. Improper use of Sto products or use as part of an improperly designed or constructed larger assembly or building may result in serious damage to this product, and to the structure of the building or its components. **STO CORP. DISCLAIMS ALL WARRANTIES EXPRESSED OR IMPLIED EXCEPT FOR EXPLICIT LIMITED WRITTEN WARRANTIES ISSUED TO AND ACCEPTED BY BUILDING OWNERS IN ACCORDANCE WITH STO'S WARRANTY PROGRAMS WHICH ARE SUBJECT TO CHANGE FROM TIME TO TIME.** For the fullest, most current information on proper application, clean-up, mixing and other specifications and warranties, cautions and disclaimers, please refer to the Sto Corp. website, www.stocorp.com.